

Comparison of Innovative Technologies for Soil Cleanup at Camp Edwards Massachusetts Military Reservation

Tri-Service Symposium




June 19, 2001

Presented by:

Katherine Weeks
Project Engineer

Massachusetts Military Reservation (MMR)

- Located on Cape Cod
- Central Impact Area, training ranges used for target practice, range training
- Covers 15,000 acres
- Surface soils
 - ° Glacial end moraine
 - ° Fine sand boulders, little clay
 - pH 5.5 to 6.0
 - Thin layer of organics



Explosives Residues in Soils at MMR

- Explosives deposition attributes
 - ° Particulates
 - ° Low concentrations
 - ° Variability in duplicate soil samples
- Soil Cleanup Goals are low to support drinking water requirements



Innovative Technology Evaluation (ITE) Who's on the ITE Team?


- Army National Guard (ARNG)
- AMEC Earth and Environmental
- Army Environmental Center
- Army Corps of Engineers New England District

What is the ITE Doing?

- Select innovative soil and groundwater remediation technologies to address explosives contamination at MMR
- Laboratory bench scale studies
- Field scale demonstrations

Why is ITE Being Done?

- Support responses to EPA Administrative Orders to protect groundwater at MMR
- Future applications at other DoD/ARNG training installations



How Were Technologies Selected?

- Selection criteria include
 - Media treated soils
 - Experience with explosives
 - ° Clean-up levels achieved
 - ° Time frame to complete clean up
- Vendors chosen based on competitive bid proposals



Technologies Selected for ITE Studies

- Physical Processes
 - Soil Washing
 - ° Low Temperature Thermal Destruction
- Biological Processes
 - Composting
 - Solid Phase Bioremediation
 - Bioslurry
- Chemical Processes
 - ° Chemical Oxidation
 - ° Chemical Reduction

Physical Process - Soil Washing Brice, Inc.

- Isolates metal particulates and soil containing most of the contaminants
- Demonstrated at MMR, reducing soils requiring further remediation by 74%
 Soil Washing at MMR
- Washed soils included in ITE studies



Photo courtesy of Brice, Inc.

Physical Process - Low Temperature Thermal Destruction - TerraTherm

Thermal Destruction in the field

- Thermally degrades contaminants by slow heating
- TerraTherm heated soil to 200°, 250°, and 300°C
- Washed and untreated soil



Photo courtesy of TerraTherm, Inc.

Biological Process - Composting BSI

- Uses local nutrients (manure, cranberry mash) and bulking agents (wood chips)
- 70% additives mixed with 30% soil
- Washed and untreated soils



Photo courtesy of BSI, Inc.

Biological Process - Solid Phase Bioremediation - Grace Canada

- **Solid Phase Bioremediation in the field**
- Uses DARAMEND® made from plant fibers
- 2% DARAMEND® added to soil
- 0.2% iron added to control redox potential
- Washed, untreated soils



Photo courtesy of Grace Canada, Inc.

Biological Process - Bioslurry Envirogen

- Adds a nutrient to a slurry (>70% water)
- 0.3% molasses added to soil
- Study is not complete

Molasses added to bioslurry



Photo courtesy of Envirogen, Inc.

Chemical Process - Oxidation Brice/UNL

- Destroys contaminants with oxidizing agents
- 1% 4% hydrogen peroxide and 80 - 320 mg iron sulfate added to soil
- Washed soil only




Chemical Process - Reduction Brice/UNL


Chemical Reduction in the Field


- Destroys
 contaminants with
 reducing agents
- 5% iron, acetic acid, aluminum sulfate added to wet soil
- Washed soils only





Photo courtesy of Brice, Inc. and University of Nebraska, Lincoln













ITE Study Results - DRAFT

Low Temperature Thermal Destruction

- For Worked on washed soils, remediates unwashed soils at higher temperatures (250° and 300°C)
- Against Not clear whether proven or disproven for HMX at 200°C
- Safety issues need to be addressed historic DoD rejection of thermal technologies



ITE Study Results - DRAFT

Composting, Solid Phase Bioremediation

- For Worked on washed soils Composting has historically worked well at many munitions manufacturing and assembly sites
- Against Difficult to prove success in unwashed soils, due to outliers



ITE Study Results - DRAFT

Chemical Reduction and Oxidation

- For Reduction worked well on washed soils
- Against Question of re-drying dissolved RDX onto soils for the study
- Oxidation not successful in washed soils

ITE Study - Next Steps

- Finalize conclusions
- Review conceptual designs for field-scale demonstration
- Recommend technologies for field-scale demonstrations